

4C30 Cyanoacrylate

Permabond cyanoacrylates are single component adhesives which polymerise rapidly when pressed into a thin film between components. Strong bonds are developed extremely quickly, making Permabond 4C30 an ideal choice for high-speed production lines for increased productivity. Permabond 4C30 is suitable for a wide range of applications on most of the plastic, rubber and metal materials used in the medical device industry. The cured material passes USP Class VI and Cytotoxicity requirements.

4C30 is ideal for use on high-speed production lines

- High Viscosity
- USP Class VI and meets cytotoxicity requirements
- Withstands ethylene oxide sterilisation and gamma irradiation

PHYSICAL PROPERTIES

Appearance	Colourless, Transparent
Viscosity @ 25°C	1500 mPa.s
Specific Gravity @ 25°C	1.05
Flashpoint	82°C
Base Compound	Ethyl Cyanoacrylate

CURED PROPERTIES

Appearance	Colourless, Transparent
Softening Point	150-170°C
Shore D Hardness	85
Dielectric Strength	10,000 volts/mm
Service Temperature	-62 to +80°C
Water Absorption	<2%
Elongation	<5%

TYPICAL PERFORMANCE

Fixture Time (Steel)	15-50 seconds
(Nitrile Rubber)	15-40 seconds
(Phenolic)	15-40 seconds
Lap Shear Strength (Steel)	14 MPa
(Aluminium)	8 MPa
(Styrene)	1 MPa (substrate failure)
(PVC)	3.6 MPa (substrate failure)
Impact Strength	4-9.5 J

Handling times can be affected by temperature, humidity and specific surfaces being bonded. Larger gaps or acidic surfaces will also reduce cure speed.

Surface Preparation

The surfaces should be clean and dry. Apply a small drop of the adhesive to one of the surfaces, join together and hold or clamp for 15-60 seconds. Do not disturb or realign the joint until the adhesive has reached handling strength. Temperature, humidity and specific surfaces being bonded can affect actual handling times.

Hard to bond surfaces such as polypropylene, polyethylene, PTFE and silicone should be surface treated before bonding, for further advice please contact the Permabond technical team.

Storage & Handling

Permabond 4C30 has a shelf life of one year when stored in a refrigerator. Refrigerated product should be allowed to warm to room temperature before opening to prevent condensation causing premature hardening of the adhesive.

Cyanoacrylates will bond skin and eyes in seconds, Contact with skin and eyes should be avoided. Use in well ventilated area. Full information may be obtained from the Material Safety Data Sheet (MSDS).

Disclaimer: PERMABOND ENGINEERING ADHESIVES LTD MAKES NO REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF THESE MATERIALS FOR USE IN IMPLANTATION IN THE HUMAN BODY, OR FOR ANY OTHER USE. These materials are not designed or manufactured for use in implantation in the human body. Permabond has not performed clinical testing of these materials for implantation. Permabond has neither sought, nor received, approval from the FDA for the use of these materials in implantation in the human body.

Non-Warranty: The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full scale production make their own satisfaction whether the product is of acceptable quality and is suitable for their particular purposes under their own operating conditions.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principle of the Chemical Manufacturers Association's Responsible Care® program.

FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN

UK Customer Service: 0800 975 9700
Germany: 0800 10 13 177

UK Helpline: 0800 975 9800
France: 0805 11 13 88

Tel. +44(0)2380 611400
Fax. +44(0)2380 611700

Permabond[®]
Engineering Adhesives

Permabond Engineering Adhesives Ltd, Wessex House
Upper Market Street, Eastleigh, SO50 9FD UK

Permabond 4C30 Cyanoacrylate